BOOTSKLEBER MIT HÄRTER

Für Verklebungen mit hoher Haftkraft und Wärmebeständigkeit.

Mischverhältnis: 10 Teile Kleber : 1 Teil Härter **Inhalt:** 42 g Kleber, 5 ml Härter

Anwendung: Die Klebeflächen müssen sauber, fettfrei und trocken sein. Die Klebeflächen reinigen und mit Schleifpapier gut aufrauhen. Kleber mit Härter im Verhältnis 10:1 mischen (Der Kleber reicht für eine Fläche von ca. 30 x 20 cm). Kleber beidseitig dünn und gleichmäßig auftragen und ca. 5 Minuten ablüften lassen. Dann die Klebeflächen passgenau zusammenfügen und kräftig anpressen

Vorsicht: Verarbeiten Sie den abgemischten Kleber innerhalb von 2 Stunden. Verwenden Sie den Kleber nicht im prallen Sonnenschein. Sorgen Sie für gute Durchlüftung in geschlossenen Räumen. Bewahren Sie den Kleber für Kinder unerreichbar auf. Verwenden Sie den Kleber nicht neben offenem Feuer.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOOTSKLEBER MIT HÄRTER

Für Verklebungen mit hoher Haftkraft und Wärmebeständigkeit.

Mischverhältnis: 10 Teile Kleber : 1 Teil Härter **Inhalt:** 42 g Kleber, 5 ml Härter

Anwendung: Die Klebeflächen müssen sauber, fettfrei und trocken sein. Die Klebeflächen reinigen und mit Schleifpapier gut aufrauhen. Kleber mit Härter im Verhältnis 10:1 mischen (Der Kleber reicht für eine Fläche von ca. 30 x 20 cm). Kleber beidseitig dünn und gleichmäßig auftragen und ca. 5 Minuten ablüften lassen. Dann die Klebeflächen passgenau zusammenfügen und kräftig anpressen

Vorsicht: Verarbeiten Sie den abgemischten Kleber innerhalb von 2 Stunden. Verwenden Sie den Kleber nicht im prallen Sonnenschein. Sorgen Sie für gute Durchlüftung in geschlossenen Räumen. Bewahren Sie den Kleber für Kinder unerreichbar auf. Verwenden Sie den Kleber nicht neben offenem Feuer.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOOTSKLEBER MIT HÄRTER

Für Verklebungen mit hoher Haftkraft und Wärmebeständigkeit.

Mischverhältnis: 10 Teile Kleber : 1 Teil Härter **Inhalt:** 42 g Kleber, 5 ml Härter

Anwendung: Die Klebeflächen müssen sauber, fettfrei und trocken sein. Die Klebeflächen reinigen und mit Schleifpapier gut aufrauhen. Kleber mit Härter im Verhältnis 10:1 mischen (Der Kleber reicht für eine Fläche von ca. 30 x 20 cm). Kleber beidseitig dünn und gleichmäßig auftragen und ca. 5 Minuten ablüften lassen. Dann die Klebeflächen passgenau zusammenfügen und kräftig anpressen

Vorsicht: Verarbeiten Sie den abgemischten Kleber innerhalb von 2 Stunden. Verwenden Sie den Kleber nicht im prallen Sonnenschein. Sorgen Sie für gute Durchlüftung in geschlossenen Räumen. Bewahren Sie den Kleber für Kinder unerreichbar auf. Verwenden Sie den Kleber nicht neben offenem Feuer.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOOTSKLEBER MIT HÄRTER

Für Verklebungen mit hoher Haftkraft und Wärmebeständigkeit.

Mischverhältnis: 10 Teile Kleber : 1 Teil Härter **Inhalt:** 42 g Kleber, 5 ml Härter

Anwendung: Die Klebeflächen müssen sauber, fettfrei und trocken sein. Die Klebeflächen reinigen und mit Schleifpapier gut aufrauhen. Kleber mit Härter im Verhältnis 10:1 mischen (Der Kleber reicht für eine Fläche von ca. 30 x 20 cm). Kleber beidseitig dünn und gleichmäßig auftragen und ca. 5 Minuten ablüften lassen. Dann die Klebeflächen passgenau zusammenfügen und kräftig anpressen

Vorsicht: Verarbeiten Sie den abgemischten Kleber innerhalb von 2 Stunden. Verwenden Sie den Kleber nicht im prallen Sonnenschein. Sorgen Sie für gute Durchlüftung in geschlossenen Räumen. Bewahren Sie den Kleber für Kinder unerreichbar auf. Verwenden Sie den Kleber nicht neben offenem Feuer.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOOTSKLEBER MIT HÄRTER

Für Verklebungen mit hoher Haftkraft und Wärmebeständigkeit.

Mischverhältnis: 10 Teile Kleber : 1 Teil Härter **Inhalt:** 42 g Kleber, 5 ml Härter

Anwendung: Die Klebeflächen müssen sauber, fettfrei und trocken sein. Die Klebeflächen reinigen und mit Schleifpapier gut aufrauhen. Kleber mit Härter im Verhältnis 10:1 mischen (Der Kleber reicht für eine Fläche von ca. 30 x 20 cm). Kleber beidseitig dünn und gleichmäßig auftragen und ca. 5 Minuten ablüften lassen. Dann die Klebeflächen passgenau zusammenfügen und kräftig anpressen

Vorsicht: Verarbeiten Sie den abgemischten Kleber innerhalb von 2 Stunden. Verwenden Sie den Kleber nicht im prallen Sonnenschein. Sorgen Sie für gute Durchlüftung in geschlossenen Räumen. Bewahren Sie den Kleber für Kinder unerreichbar auf. Verwenden Sie den Kleber nicht neben offenem Feuer.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOOTSKLEBER MIT HÄRTER

Für Verklebungen mit hoher Haftkraft und Wärmebeständigkeit.

Mischverhältnis: 10 Teile Kleber : 1 Teil Härter **Inhalt:** 42 g Kleber, 5 ml Härter

Anwendung: Die Klebeflächen müssen sauber, fettfrei und trocken sein. Die Klebeflächen reinigen und mit Schleifpapier gut aufrauhen. Kleber mit Härter im Verhältnis 10:1 mischen (Der Kleber reicht für eine Fläche von ca. 30 x 20 cm). Kleber beidseitig dünn und gleichmäßig auftragen und ca. 5 Minuten ablüften lassen. Dann die Klebeflächen passgenau zusammenfügen und kräftig anpressen

Vorsicht: Verarbeiten Sie den abgemischten Kleber innerhalb von 2 Stunden. Verwenden Sie den Kleber nicht im prallen Sonnenschein. Sorgen Sie für gute Durchlüftung in geschlossenen Räumen. Bewahren Sie den Kleber für Kinder unerreichbar auf. Verwenden Sie den Kleber nicht neben offenem Feuer.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOAT GLUE WITH HARDENING AGENT

For gluing operations that require high adhesive power and resistance to heat.

Mixing ratio: 10 parts of glue: 1 part of hardening agent **Contents** 42 gr. glue, 5 ml. hardening agent

Application: The surfaces to be glued must be clean, dry and free of grease. Clean both surfaces and roughen them well with abrasive paper. Mix both the glue to the hardening agent to the ratio of 10:1 (the product will be enough for a surface of about 30 x 20 cm.). Apply a thin and even layer of glue on both surfaces and let them air for about five minutes. After that join both surfaces together and press them tightly against each other.

Caution: The mixed product must be used within two hours. Do not use the glue in full sun exposure. Ensure good air circulation in closed rooms. Keep glue away from children. Do not use glue near on open flame.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOAT GLUE WITH HARDENING AGENT

For gluing operations that require high adhesive power and resistance to heat.

Mixing ratio: 10 parts of glue: 1 part of hardening agent **Contents** 42 gr. glue, 5 ml. hardening agent

Application: The surfaces to be glued must be clean, dry and free of grease. Clean both surfaces and roughen them well with abrasive paper. Mix both the glue to the hardening agent to the ratio of 10:1 (the product will be enough for a surface of about 30 x 20 cm.). Apply a thin and even layer of glue on both surfaces and let them air for about five minutes. After that join both surfaces together and press them tightly against each other.

Caution: The mixed product must be used within two hours. Do not use the glue in full sun exposure. Ensure good air circulation in closed rooms. Keep glue away from children. Do not use glue near on open flame.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOAT GLUE WITH HARDENING AGENT

For gluing operations that require high adhesive power and resistance to heat.

Mixing ratio: 10 parts of glue: 1 part of hardening agent **Contents** 42 gr. glue, 5 ml. hardening agent

Application: The surfaces to be glued must be clean, dry and free of grease. Clean both surfaces and roughen them well with abrasive paper. Mix both the glue to the hardening agent to the ratio of 10:1 (the product will be enough for a surface of about 30 x 20 cm.). Apply a thin and even layer of glue on both surfaces and let them air for about five minutes. After that join both surfaces together and press them tightly against each other.

Caution: The mixed product must be used within two hours. Do not use the glue in full sun exposure. Ensure good air circulation in closed rooms. Keep glue away from children. Do not use glue near on open flame.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOAT GLUE WITH HARDENING AGENT

For gluing operations that require high adhesive power and resistance to heat.

Mixing ratio: 10 parts of glue: 1 part of hardening agent **Contents** 42 gr. glue, 5 ml. hardening agent

Application: The surfaces to be glued must be clean, dry and free of grease. Clean both surfaces and roughen them well with abrasive paper. Mix both the glue to the hardening agent to the ratio of 10:1 (the product will be enough for a surface of about 30 x 20 cm.). Apply a thin and even layer of glue on both surfaces and let them air for about five minutes. After that join both surfaces together and press them tightly against each other.

Caution: The mixed product must be used within two hours. Do not use the glue in full sun exposure. Ensure good air circulation in closed rooms. Keep glue away from children. Do not use glue near on open flame.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOAT GLUE WITH HARDENING AGENT

For gluing operations that require high adhesive power and resistance to heat.

Mixing ratio: 10 parts of glue: 1 part of hardening agent **Contents** 42 gr. glue, 5 ml. hardening agent

Application: The surfaces to be glued must be clean, dry and free of grease. Clean both surfaces and roughen them well with abrasive paper. Mix both the glue to the hardening agent to the ratio of 10:1 (the product will be enough for a surface of about 30 x 20 cm.). Apply a thin and even layer of glue on both surfaces and let them air for about five minutes. After that join both surfaces together and press them tightly against each other.

Caution: The mixed product must be used within two hours. Do not use the glue in full sun exposure. Ensure good air circulation in closed rooms. Keep glue away from children. Do not use glue near on open flame.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOAT GLUE WITH HARDENING AGENT

For gluing operations that require high adhesive power and resistance to heat.

Mixing ratio: 10 parts of glue: 1 part of hardening agent **Contents** 42 gr. glue, 5 ml. hardening agent

Application: The surfaces to be glued must be clean, dry and free of grease. Clean both surfaces and roughen them well with abrasive paper. Mix both the glue to the hardening agent to the ratio of 10:1 (the product will be enough for a surface of about 30 x 20 cm.). Apply a thin and even layer of glue on both surfaces and let them air for about five minutes. After that join both surfaces together and press them tightly against each other.

Caution: The mixed product must be used within two hours. Do not use the glue in full sun exposure. Ensure good air circulation in closed rooms. Keep glue away from children. Do not use glue near on open flame.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**

BOAT GLUE WITH HARDENING AGENT

For gluing operations that require high adhesive power and resistance to heat.

Mixing ratio: 10 parts of glue: 1 part of hardening agent **Contents** 42 gr. glue, 5 ml. hardening agent

Application: The surfaces to be glued must be clean, dry and free of grease. Clean both surfaces and roughen them well with abrasive paper. Mix both the glue to the hardening agent to the ratio of 10:1 (the product will be enough for a surface of about 30 x 20 cm.). Apply a thin and even layer of glue on both surfaces and let them air for about five minutes. After that join both surfaces together and press them tightly against each other.

Caution: The mixed product must be used within two hours. Do not use the glue in full sun exposure. Ensure good air circulation in closed rooms. Keep glue away from children. Do not use glue near on open flame.

GRABNER GMBH,3350 -HAAG, Weistracherstraße 11, AUSTRIA **www.grabner-sports.at**